



CARTELL CHEMICAL CO., LTD.

No.18 Cheng Gong Street, Min-Shyong Industrial Park
Chia-Yi Hsien, 621 Taiwan

TEL:886-5-220-3715 FAX:886-5-220-3720 E-MAIL sales@mxbon.com

PRODUCT TECHNICAL DATA SHEET

MXBON® 407

General Purpose - Electronic

1. PRODUCT DESCRIPTION

MXBON® 407 is a fast curing, medium viscosity industrial grade Cyanoacrylate adhesive useful for electronic applications. It has been specially formulated to achieve the strongest possible bonds such as tacking electronic parts. **MXBON® 407** is a one-component, solvent-free system and can be used with **MXBON® branded Accelerators** to achieve the desired results.

2. TYPICAL PROPERTIES OF UNCURED MATERIAL

Base	Ethyl Cyanoacrylate
Color	Transparent, colorless to yellowish colored liquid
Specific Gravity @ 25°C	1.05
Flash Point	See MSDS
Viscosity (cP) , 25°C	700 – 1000

3. CURING PERFORMANCE

There are many factors that can influence the rate of cure. These include: the types of substrate used, the condition of the surface to be bonded, the smoothness of the surface, the closeness of the surfaces, the atmospheric conditions etc.

Cure Speed / substrate

Steel to Steel	15 – 30 seconds
Stainless Steel	30 – 90 seconds
Aluminum	10 – 25 seconds
Zinc plated	30 – 90 seconds
ABS to ABS	15 – 50 seconds
ABS to NBR	10 – 15 seconds
ABS to Wood	15 – 30 seconds
NBR to NBR	3 – 10 seconds
Polycarbonate	20 – 60 seconds

Cure Speed / Bond Gap

The rate of cure depends on the bond-gap. A smaller bond-gap results in faster cure speeds.

4. TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties	
Color	Clear
Coefficient of Thermal Expansion (K ⁻¹)	80 x 10 ⁻⁵
Coefficient of Thermal Conductivity (W/m.K)	10
Working Temperature	-50°C ~ 80 °C
Electrical Properties	
Volume Resistivity (Ω.cm)	7.2 x 10 ¹⁵
Surface Resistivity (Ω)	66 x 10 ¹⁵
Dielectric Constant @ 10 kHz	2.30
Dielectric Dissipation Factor @ 10 kHz	<0.02
Dielectric Breakdown Strength (kV/mm)	36.60

5. ADHESIVE PERFORMANCE

After 24 hours at 25°C.

Tensile Strength	
Steel	190 – 210 Kg/ cm ²
Stainless Steel	250 – 450 Kg/ cm ²
Aluminum	170 – 190 Kg/ cm ²
Copper	150 – 170 Kg/ cm ²
PVC	40 – 60 Kg/ cm ²
ABS	50 – 70 Kg/ cm ²
Polycarbonate	80 – 120 Kg/ cm ²
Polystyrene	30 – 45 Kg/ cm ²
NBR	5 – 9 Kg/ cm ²
SBR	5 – 10 Kg/ cm ²

6. DIRECTIONS FOR USE

1. Make sure the surfaces to be bonded are clean and dry (preferable to solvent-wipe plastics, glass, and rubber, and to acid-treat metals).

Note: Because the solvent base of **MXBON® Accelerators** can affect certain plastics or coatings, checking all surfaces for compatibility is recommended.

2. Apply **MXBON® Accelerator** to the area to be bonded. Allow sufficient time for evaporation [15 seconds]. Dispense **MXBON® 407** immediately. Apply only enough to leave a thin film after compression.

3. Hold firmly in place for a few seconds. Good contact is essential. Allow the surfaces to fixture before any further handling. An adequate bond develops in less than one minute. (Maximum strength is achieved in 24 to 48 hours).

4. Wipe off excess adhesive from the top of the container and recap **MXBON® 407** if left uncapped, may deteriorate by contamination from moisture in the air.

5. Because **MXBON® 407** condenses by polymerization, sometimes whitening will occur on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with acetone.

7. HANDLING AND STORAGE

Storage: Keep products in the unopened container in a cool and dry location. Best when stored at 2 to 8°C. Temperatures less than 2°C can adversely affect product properties. Do Not Freeze. Keep container tightly closed until ready for use.

Handling: Material removed from containers may be contaminated during use. Do not pour back any product to the original container. Misuse of product will void all warranties.

8. PRECAUTIONS

1. Use with proper ventilation. Avoid contact with skin and eyes.
2. If contact with skin occurs, rinse with warm water or dissolve gradually with solvent such as acetone, or nitromethane.
Do not try to remove forcibly.
3. If adhesive gets into eye, keep eye open and rinse thoroughly. Seek medical attention immediately.
4. Keep well out of reach of children.
5. Keep adhesive in a cool, dry place 20-25°C (68-77°F). For long-term storage, refrigeration (2°C or 35°F) is recommended.

Disclaimer: The data contained herein are furnished for informational purposes only and are believed to be reliable. However, CARTELL CHEMICAL CO., LTD. does not assume responsibility for any results obtained by persons over whose methods CARTELL CHEMICAL CO., LTD. has no control. It is the user's responsibility to determine the suitability of Cartell's products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any Cartell's products. CARTELL CHEMICAL CO., LTD. specifically disclaims all warranties express or implied, including warranties of salability and suitability for a particular purpose arising from sale or use of Cartell's products. CARTELL CHEMICAL CO., LTD. further disclaims any liability for consequential or incremental damages of any kind including lost profits.

Revision Date: April 01, 2014

Revision: 0004